

Data table - Technical specifications, typical values

	90	100	110	120	130	140	160
Grammage , g/m ² , ISO 536, ± 3%	90	100	110	120	130	140	160
Grammage Avant Performance , g/m ² , ISO 536, ± 3%	89	98	108	118	128	137	156
Moisture , %, ISO 287, ± 1,5%	8	8	8	8	8	8	8
Burst , kPa, ISO 2758	215	250	280	310	335	361	418
SCT CD , kN/m, ISO 9895	1,7	1,88	2,05	2,25	2,41	2,60	2,95
Tensile stiffness MD , kN/m, ISO 1924-2	710	750	850	950	990	1030	1100
Tensile stiffness CD , kN/m, ISO 1924-2	210	220	240	260	280	300	340
Cobb 60 (top side) , g/m ² , ISO 535	< 35,0	< 35,0	< 35,0	< 35,0	< 35,0	< 35,0	< 35,0
Colour, (L* a* b*) , ISO 5631-2	L* 58,5 ± 1,5 a* 8,0 ± 0,7 b* 20,5 ± 0,7						

Test climate 23°C±1C°/50%±2% RH (according to ISO 187)

Reel core size: 10 cm

Ideal storage conditions: 23°C/50% RH

Paper should be stored in a dry, covered and ventilated warehouse. It is recommended that prior to use in production, paper should be stored some time in conditions similar to the conditions in the production hall. The required storage period depends mainly on the volume of paper reel, as well as the temperature difference between the warehouse and production hall.

Producing mill: Ostroleka, Poland

Certificates

- ISO 9001
- ISO 14001
- OHSAS 18001
- FSC Chain of Custody
- PEFC Chain of Custody

Updated on 23rd of August 2018

